



Valve Regulated Lead Acid Battery

Maintenance-Free Sealed Lead Acid Battery.

Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99%.

Design for Standby Power Applications at Extreme Temperatures

【Design Life】

Up to 12 Years in Standby Service at 25°C

Eurobat (20°C) : 10-12 years, Long Life

【Operating Temperature Range】

Nominal Operating Temperature : 25°C (77°F)

Discharge : -20°C ~ 50°C (-4°F~122°F)

Charge: -20°C ~ 50°C (-4°F~122°F)

Storage: -15°C ~ 40°C (5°F~104°F)

【Float Charging Voltage】

13.5 ~ 13.8 VDC/Unit at 25°C (77°F)

【Equalization Charging Voltage】

14.4 ~ 15.0 VDC/Unit at 25°C (77°F)

【Self Discharge】


Less than 10% after 90 days, can be stored up to 6 months at 25°C (77°F);

Fully recharging is required before usage, and charged sooner if stored at higher temperature than 25°C (77°F).

Specification

Design according with IEC 61056-1/2:2012

Nominal Voltage	12V (6 cells per unit)	
Nominal Capacity	8.5 Ah @20hr-rate to 1.75V per cell @25°C (77°F)	
Weight	Approx. 2.62 Kg (5.78 lbs)	
Maximum Discharge Current	130A (5sec)	
Internal Resistance	Approx. 21.0 mΩ	
Short Circuit Current	288	
Maximum Charge Current	2.55A	
Terminal types	F2 terminal -Faston Tab 250	
Terminal breaking Torque	--	
Container Material	ABS (UL 94-HB) & Flame Retardant (94-V0) available upon request	
Dimensions	Length (L)	150.9±2.0 mm 5.94±0.08 inch
	Width (W)	64.8±1.0 mm 2.55±0.04 inch
	Container Height (h)	94.3±1.0 mm 3.71±0.04 inch
	Overall Height (H)	98.6±1.0 mm 3.88±0.04 inch



Constant Current Discharge Characteristics Unit: A (25°C, 77°F)

F.V/Time	5MIN	10MIN	15MIN	30MIN	60MIN	90MIN	2HR	3HR	5HR	8HR	10HR	20HR
1.60V	35.9	22.3	16.5	9.70	5.65	4.12	3.27	2.35	1.53	1.02	0.839	0.448
1.67V	34.1	21.8	16.3	9.64	5.62	4.10	3.25	2.34	1.52	1.01	0.834	0.446
1.70V	33.1	21.5	16.1	9.58	5.60	4.09	3.24	2.33	1.51	1.01	0.830	0.444
1.75V	30.8	20.6	15.7	9.42	5.53	4.05	3.21	2.31	1.50	1.00	0.823	0.440
1.80V	27.9	19.2	14.8	9.12	5.40	3.97	3.15	2.27	1.47	0.984	0.808	0.433
1.85V	25.0	17.4	13.5	8.59	5.13	3.80	3.02	2.19	1.42	0.945	0.777	0.416

Constant Power Discharge Characteristics Unit: W (25°C, 77°F)

F.V/Time	5MIN	10MIN	15MIN	30MIN	60MIN	90MIN	2HR	3HR	5HR	8HR	10HR	20HR
1.60V	374	243	185	111	65.2	47.8	37.9	27.4	18.1	12.1	9.88	5.31
1.67V	360	239	183	110	65.0	47.7	37.8	27.3	18.0	12.0	9.84	5.29
1.70V	351	236	182	109	64.8	47.6	37.7	27.2	17.9	11.9	9.82	5.28
1.75V	332	228	177	108	64.2	47.3	37.5	27.0	17.8	11.8	9.75	5.24
1.80V	308	216	168	105	62.9	46.5	36.9	26.7	17.5	11.7	9.61	5.17
1.85V	273	200	155	100	60.3	44.8	35.6	25.8	17.0	11.3	9.29	4.99

Issued: 180420

Sales Offices

日立化成能源科技股份有限公司
Hitachi Chemical Energy Technology Co., Ltd.

BUSINESS HEADQUARTERS

Tel: +886-2-2880-5600

Fax: +886-2-2888-3300

USA OFFICE

Tel: +1-817-244-7777 / 1-(800)3-CSB-USA (272872)

Fax: +1-817-244-4445

SHENZHEN OFFICE (CHINA)

Tel: +86-755-8831-6488, 8831-6775

Fax: +86-755-8831-6075

EUROPE (EMEA) OFFICE

Tel: +31(0)180-418-140

Fax: +31(0)180-418-327

SHANGHAI OFFICE (CHINA)

Tel: +86-21-5046-1622, 5046-0833

Fax: +86-21-5046-1046

TAIPEI OFFICE

Tel: +886-2-2880-5600

Fax: +886-2-2888-3300

BEIJING OFFICE (CHINA)

Tel: +86-10-5820-5336, 5820-5338

Fax: +86-10-5820-3053

Recognized under UL 1989,
and certified by ISO 9001, 14001.

